





92-103 Lodz, 5/15 Brzezinska Str., phone 48 42 6163142, fax 48 42 6792638 90-520 Lodz, 118 Gdanska Str., phone 48 42 2534419, fax 48 42 2534490

e-mail: bwitkowska@iw.lodz.pl , jandrysiak@iw.lodz.pl

LABORATORY OF TESTING TEXTILE RAW MATERIALS AND FABRICS Testing Laboratory accredited by the Polish Centre for Accreditation

TEST CERTIFICATE NO. BM 641.2/2018/G/A

- 1. Test ordered by: ,,TOPTEXTIL" Sp. z o.o. 30-415 Kraków, ul. Wadowicka 12
- 2. Name and description of tested material: sample mattress fabric NAPOLI; declared raw materials: 100% Polvester
- 3. Date of receiving material for testing: 2018-12-20
- 4. Date of test performance: 2018-12-28÷31
- 5. Samples taken by: correct sample size in appropriate state for testing, taken by the Client and delivered without the Sampling Protocol
- 6. Tests carried out according to: methods presenting in testing table

Results of Laboratory Tests

see page 2/2

Test performed by: Krystyna Wierus M.Sc. Eng

- 1. Test results refer only to the tested material.
- 2. Neither of the parts of this Test Certificate can be copied without written permission of the Head of the Laboratory; i can be copied only as a whole document.
- 3. Test Certificate presents test results included within accreditation field of testing.
- 4. Test results not included in accreditation scope, if occur, are marked with *) in the test results table, at the parameter name.
- 5. Measurement uncertainty, if it is specified, has been determined according to the recommendations presented in document EA-4/16. Presented values of uncertainty constitute expanded uncertainty at 95% confidence level and coverage factor k = 2. INSTYTUT WEOKIE TOTCTWA

Certificate date: 2019-01-03 **Number of Certificate copies: 4 Test Certificate handed to:**

- 1) "TOPTEXTIL" Sp. z o.o.- 2 copies.,
- 2) Laboratory for Testing Textile Raw Materials and Fabrics (location: 5/15 Brzezińska str.) 1 copy,
- 3) Laboratory for Testing Textile Raw Materials and Fabrics (location: 118 Gdańska str.) 1 copy.

Certificate prepared by:

Zofia Mokwińska M.Sc. Eng

Person authorizing the Test Certificate:

Surname and name: Beata Witkowska, Ph. D.

Surname and maine. Dealer Surowcov. Function. Florid of Punction Wickienniczych Signature:

dr int. Beata Witkowska

LABORATORIUM B. DAN WYROBÓW WŁ SKIE!

92-103 Łódź, ul. Brze:

Siedziba 90-520 Łóc. tel. 42 25 34 419, fax 4.

TEST CERTIFICATE NO. BM 641.2 / 2018 / G / A

Parameter	Value	Remarks			
Dimensional change after one washing and drying, %		PN-EN ISO 5077:2011 PN-EN ISO 3759:2011			
-lengthwise direction, %	$-5,5 \pm 0,5$	number of washings / washing			
-widthwise direction, %	$-2,5 \pm 0,0$	procedure number / drying procedure according to PN-EN ISO 6330:2012			
		1 x / 6N at temperature 60°C /			
51		procedure A –line dry,			
		number of samples -3 , mass of the			
		samples – 153 g, type of ballast: - III,			
		reference detergent 3,the washer type A, (-) shrinkage, (+) extension.			

The end of Tes	t Cartificata
The chu of Tes	i Cerinicate

Person authorizing the Test Certificate

Laboratorium Badań Surowców i Wyrobów Włókienniczych KIEROWNIK

dr inż. Beata Witkowska



Laboratory of Testing Textile Ecology and Work Environment

PCA
POLSKIE CENTRUM
AKREDYTACJI
BADANIA

AB 1401

I ŚRODOWISKA PRAC

90-520 Łódź, ul. Gdańska 118 tel. 42 25 34 422, fax 42 25 34 490

LABORATORIUM BA

Textile Research Institute, 92-103 Lodz, 5/15 Brzezinska Str.
Laboratory: 90-520 Lodz, 118 Gdanska Str., phone 48 42 2534422, 48 42 2534425, fax 48 42 2534490

e-mail: ekologia@iw.lodz.pl

TEST CERTIFICATE No. 7.3 / ODPRAN / BE /19

Orderer:

Toptextil Sp. z o.o.

ul. Wadowicka 12

30-415 Kraków

Testing method:

PN-EN ISO 105-C06:2010 Textiles. Tests for colour fastness.

Part C06: Colour fastness to domestic and commercial laundering.

Subject of test:

sample - mattress fabric NAPOLI;

declared raw materials: 100% Polyester

Sampled and delivered by orderer, in a proper condition for test.

Test results:

TESTED PARAMETER	Determination [Grading]										
Colour fastness to:	Change in colour	Staining									
		WO	PAN	PES	PA	CO	CA	CV			
Washing	5	-	-	5	-	5	-	-			
Methods number	C1S (60 °C)										
Quantity of steel's small balls	25										
Reference detergent	recommended by ECE										

The test results refer to testing conditions of the method.

The colour fastness rating goes gradually from: rating 5 - no contrast (best rating) to rating 1 - large contrast (worst rating). Possible values of the gray scale: 5, 4-5, 4, 3-4, 3, 2-3, 2, 1-2, 1.

Test carried out by:

mgr inż. Agnieszka Kaleta

Sample delivered at:

2019-01-03

Test finished at:

2019-01-09

Authorized Test Certificate:

E-BORATORIUM BADAŃ EKOLOGII TEKSTYLIÓW

NOTES:

- 1. The test certificate results only refer to the sample material provided.
- 2. The test certificate contains 1 page.
- 3. The test certificate shall not be reproduced, except in full, without the written approval of Testing Laboratory.
- 4. Orderer shall be responsible for the conformity of product with the test sample, where the test certificate is used.